



MACpropy 629TC MP 318N Century 6 HD White

FACE MATERIAL

MACpropy 629 T.C. is a white gloss polypropylene film, biaxially oriented, with a print receptive acrylic top-coating.

Showing good conversion and application properties.
High opacity, good heat and traction resistance.

Application

This product is mainly used for production of labels for cosmetics, household and pharmaceutical products (vials, ampoules, syringes, etc.). Good stiffness.

Technical characteristics

Thickness	60 ± 6 µm	ISO 534
Weight	45 ± 5 gr/m ²	ISO 536
Tensile strength MD	≥ 70 N/15mm	DIN 53455
Resistance CD	≥ 120 N/15mm	DIN 53455
Glossy	≥ 65%	DIN 67530
Opacity	≥ 80%	DIN 53146

ADHESIVE

A clear permanent acrylic adhesive with high ultraviolet and weathering resistance. Non staining adhesive. Optical clarity.

Good resistance to chemicals and heat.
MP 318N offers excellent adhesion properties and cohesive strength, with inherent resistance to stringing allowing excellent convertibility. MP318N complies with REACH regulation.

Properties

High Speed Release	0,59 ± 0,10	N/25mm at 100 m/min.	FTM 4
Low Speed Release	0,11 ± 0,05	N/25mm at 300 mm/min	FTM 3
Quick Tack	≥ 11	N/25 mm on glass	FTM 9
Final Peel (20 min)	≥ 8	N/25 mm on glass	FTM 1
Cohesion	≥ 100	Hours on glass	FTM 8
Appl. temperature	≥ 0°C		
Service temperature	from -20 to +90°C		

BACKING

High density, super calendered glassine backing paper. Constant calliper, good strength properties and even compressibility (die-cutting ability). Good translucency for optical scanning.

Technical characteristics

Thickness	55 ± 4 µm	ISO 534
Weight	65 ± 4 gr/m ²	ISO 536
Tensile strength MD	Typ. Value 90 N/15 mm	DIN 53455
Resistance CD	Typ. Value 55 N/15 mm	DIN 53455
Transparency	≥ 48 %	DIN 53147

Shelf life : 3 years when stored at 15-25°C, (50+/-5) % relative humidity, in the original packaging.



MACtac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.